



## TECHNICAL SPECIFICATION SHEET

Range

Arran

Design

Flat woven, dobby

Composition  $\pm 3\%$  per compound

100% Polyester

Useable Fabric Width (cm)

138

Pattern Repeat (cm)

Vertical	17.1	Horizontal	15.5
----------	------	------------	------

Martindale (rubs)

$\geq 45,000$

Seam (mm)

Warp	$\leq 4\text{mm}$	Weft	$\leq 3\text{mm}$
------	-------------------	------	-------------------

Tensile (N)

Warp	$\geq 1400\text{N}$	Weft	$\geq 700\text{N}$
------	---------------------	------	--------------------

Tear (N)

Warp	$\geq 130\text{N}$	Weft	$\geq 90\text{N}$
------	--------------------	------	-------------------

Pilling Grade

@2000 rubs	$\geq 4$	@5000 rubs	$\geq 3-4$
------------	----------	------------	------------

Bursting (kPa)

n/a

Weight (gsm)  $\pm 5\%$

300

FR Weight (gsm)  $\pm 5\%$

UK	380	SIAN	430
----	-----	------	-----

FR Chemical Reference

UK	FP-1956	SIAN	SA-860B-1
----	---------	------	-----------

Care Instructions

Professional dry clean in situ only



>

<