



TECHNICAL SPECIFICATION SHEET

Range

| | | | |
|----------|--|--|--|
| Opulence | | | |
|----------|--|--|--|

Design

| | | | |
|-------------------------|--|--|--|
| Knitted, non woven pile | | | |
|-------------------------|--|--|--|

Composition $\pm 3\%$ per Compound

| | | | |
|----------------|--|--|--|
| 100% Polyester | | | |
|----------------|--|--|--|

Useable Fabric Width (cm)

| | | | |
|-------|--|--|--|
| 138cm | | | |
|-------|--|--|--|

Pattern Repeat (cm)

| | | | |
|----------|-----|------------|-----|
| Vertical | n/a | Horizontal | n/a |
|----------|-----|------------|-----|

Martindale (rubs)

| | | | |
|---------|--|--|--|
| >45,000 | | | |
|---------|--|--|--|

Seam (mm)

| | | | |
|------|-----|------|-----|
| Warp | n/a | Weft | n/a |
|------|-----|------|-----|

Tensile (N)

| | | | |
|------|-----|------|-----|
| Warp | n/a | Weft | n/a |
|------|-----|------|-----|

Tear (N)

| | | | |
|------|-----|------|-----|
| Warp | n/a | Weft | n/a |
|------|-----|------|-----|

Pilling Grade

| | | | |
|-------------|---|-------------|---|
| @ 2000 rubs | 5 | @ 5000 rubs | 5 |
|-------------|---|-------------|---|

Bursting (kPa)

| | | | |
|----------------|--|--|--|
| ≥ 400 kPa | | | |
|----------------|--|--|--|

Weight (gsm) $\pm 5\%$

| | | | |
|-----|--|--|--|
| 260 | | | |
|-----|--|--|--|

FR Weight (gsm) $\pm 5\%$

| | | | |
|----|-----|------|-----|
| UK | 350 | SIAN | 390 |
|----|-----|------|-----|

FR Chemical Reference

| | | | |
|----|--------|------|----------|
| UK | FP2366 | SIAN | SA-5289B |
|----|--------|------|----------|

Care Instructions

| | | | |
|-------------------------------------|--|--|--|
| Professional dry clean in situ only | | | |
|-------------------------------------|--|--|--|

