



TECHNICAL SPECIFICATION SHEET

Range

Linnet

Design

Flat woven

Composition $\pm 3\%$ per Compound

100% polyester

Useable Fabric Width (cm)

138

Pattern Repeat (cm)

Vertical	n/a	Horizontal	n/a
----------	-----	------------	-----

Martindale (rubs)

>45,000

Seam (mm)

Warp	$\leq 3\text{mm}$	Weft	$\leq 3\text{mm}$
------	-------------------	------	-------------------

Tensile (N)

Warp	$\geq 900\text{N}$	Weft	$\geq 900\text{N}$
------	--------------------	------	--------------------

Tear (N)

Warp	$\geq 60\text{N}$	Weft	$\geq 50\text{N}$
------	-------------------	------	-------------------

Pilling Grade

@2000 rubs	4	@5000 rubs	4
------------	---	------------	---

Bursting (kPa)

n/a

Weight (gsm) $\pm 5\%$

310

FR Weight (gsm) $\pm 5\%$

UK	360	SIAN	360
----	-----	------	-----

FR Chemical Reference

UK	GreenFR®	SIAN	GreenFR®
----	----------	------	----------

Care Instructions

Professional dry clean in situ only

