



TECHNICAL SPECIFICATION SHEET

Range

Ansell

Design

Flat woven, Chenille

Composition $\pm 3\%$ per compound

100% rPET

Useable Fabric Width (cm)

138

Martindale (rubs)

> 50,000

Seam (mm)

Warp	$\leq 2\text{mm}$	Weft	$\leq 2\text{mm}$
------	-------------------	------	-------------------

Tensile (N)

Warp	$\geq 1000\text{N}$	Weft	$\geq 750\text{N}$
------	---------------------	------	--------------------

Tear (N)

Warp	$\geq 60\text{N}$	Weft	$\geq 40\text{N}$
------	-------------------	------	-------------------

Pilling Grade

@2000 rubs	4-5	@5000 rubs	4-5
------------	-----	------------	-----

Bursting (kPa)

n/a

Weight (gsm) $\pm 5\%$

460

FR Weight (gsm) $\pm 5\%$

UK	540	SIAN	570
----	-----	------	-----

Care Instructions

Professional dry clean in situ only

