



TECHNICAL SPECIFICATION SHEET

Range

Dalton

Design

Flat woven

Composition $\pm 3\%$ per compound

100% Polyester

Useable Fabric Width (cm)

138

Martindale (rubs)

$\geq 45,000$

Seam (mm)

Warp	$\leq 3\text{mm}$	Weft	$\leq 4\text{mm}$
------	-------------------	------	-------------------

Tensile (N)

Warp	$\geq 800\text{N}$	Weft	$\geq 1200\text{N}$
------	--------------------	------	---------------------

Tear (N)

Warp	$\geq 50\text{N}$	Weft	$\geq 120\text{N}$
------	-------------------	------	--------------------

Pilling Grade

@2000 rubs	4	@5000 rubs	4
------------	---	------------	---

Bursting (kPa)

N/A

Weight (gsm) $\pm 5\%$

260

FR Weight (gsm) $\pm 5\%$

UK	360	SIAN	n/a
----	-----	------	-----

Care Instructions

Professional dry clean in situ only			
-------------------------------------	--	--	--

--	--	--	--	--