



TECHNICAL SPECIFICATION SHEET

Range

Hampton

Design

Flat Woven

Composition $\pm 3\%$ per Compound

100% Polyester

Useable Fabric Width (cm)

138

Martindale (rubs)

>50,000

Seam (mm)

Warp	$\leq 4\text{mm}$	Weft	$\leq 3\text{mm}$
------	-------------------	------	-------------------

Tensile (N)

Warp	$\geq 1000\text{N}$	Weft	$\geq 700\text{N}$
------	---------------------	------	--------------------

Tear (N)

Warp	$\geq 100\text{N}$	Weft	$\geq 80\text{N}$
------	--------------------	------	-------------------

Pilling Grade

@ 2000	4-5	@ 5000	4
--------	-----	--------	---

Bursting (kPa)

n/a

Weight (gsm) $\pm 5\%$

340

FR Weight (gsm) $\pm 5\%$

UK	450	SIAN	480
----	-----	------	-----

Care Instructions

Professional dry clean in situ only

