



TECHNICAL SPECIFICATION SHEET

Range

Hopsack

Design

Flat woven Chenille

Composition $\pm 3\%$ per Compound

100% Polyester

Useable Fabric Width (cms)

138

Martindale (rubs)

>70,000

Seam (mm)

Warp	$\leq 2\text{mm}$	Weft	$\leq 2\text{mm}$
------	-------------------	------	-------------------

Tensile (N)

Warp	$\geq 1100\text{N}$	Weft	$\geq 1300\text{N}$
------	---------------------	------	---------------------

Tear (N)

Warp	$\geq 190\text{N}$	Weft	$\geq 250\text{N}$
------	--------------------	------	--------------------

Pilling Grade

@2000	4	@5000	4
-------	---	-------	---

Bursting (kPa)

n/a

Weight (gsm) $\pm 5\%$

530

FR Weight (gsm) $\pm 5\%$

UK	630	SIAN	660
----	-----	------	-----

Care Instructions

Professional dry clean in situ only

