



TECHNICAL SPECIFICATION SHEET

Range

Lisette

Design

Flat woven

Composition $\pm 3\%$ per compound

52% Polyester, 48% Cotton

Useable Fabric Width (cm)

138

Martindale (rubs)

>100,000

Seam (mm)

Warp	$\leq 2\text{mm}$	Weft	$\leq 2\text{mm}$
------	-------------------	------	-------------------

Tensile (N)

Warp	$\geq 1500\text{N}$	Weft	$\geq 700\text{N}$
------	---------------------	------	--------------------

Tear (N)

Warp	$\geq 75\text{N}$	Weft	$\geq 45\text{N}$
------	-------------------	------	-------------------

Pilling Grade

@2000 rubs	4	@5000 rubs	3-4
------------	---	------------	-----

Bursting (kPa)

n/a

Weight (gsm) $\pm 5\%$

370

FR Weight (gsm) $\pm 5\%$

UK	430	SIAN	n/a
----	-----	------	-----

Care Instructions

Professional dry clean in situ only

