



## TECHNICAL SPECIFICATION SHEET

Range

**Malmö**

Design

Textured Chenille

Composition  $\pm 3\%$  per Compound

100% Polyester

Useable Fabric Width (cm)

138

Martindale (rubs)

>50,000

Seam (mm)

Warp	$\leq 2\text{mm}$	Weft	$\leq 4\text{mm}$
------	-------------------	------	-------------------

Tensile (N)

Warp	$\geq 1200\text{N}$	Weft	$\geq 500\text{N}$
------	---------------------	------	--------------------

Tear (N)

Warp	$\geq 100\text{N}$	Weft	$\geq 50\text{N}$
------	--------------------	------	-------------------

Pilling Grade

@2000 rubs	4	@5000 rubs	4
------------	---	------------	---

Bursting (kPa)

n/a

Weight (gsm)  $\pm 5\%$

360

FR Weight (gsm)  $\pm 5\%$

UK	460	SIAN	480
----	-----	------	-----

Care Instructions

Professional dry clean in situ only

