



TECHNICAL SPECIFICATION SHEET

Range

Marlon

Design

Flat Woven, Chenille			
----------------------	--	--	--

Composition $\pm 3\%$ per compound

100% rPET			
-----------	--	--	--

Useable Fabric Width (cm)

138			
-----	--	--	--

Martindale (rubs)

$>65,000$			
-----------	--	--	--

Seam (mm)

Warp	$\leq 2\text{mm}$	Weft	$\leq 2\text{mm}$
------	-------------------	------	-------------------

Tensile (N)

Warp	$\geq 2000\text{N}$	Weft	$\geq 1000\text{N}$
------	---------------------	------	---------------------

Tear (N)

Warp	$\geq 70\text{N}$	Weft	$\geq 50\text{N}$
------	-------------------	------	-------------------

Pilling Grade

@2000 rubs	4-5	@5000 rubs	4-5
------------	-----	------------	-----

Bursting (kPa)

n/a			
-----	--	--	--

Weight (gsm) $\pm 5\%$






460			
-----	--	--	--

FR Weight (gsm) $\pm 5\%$

UK	550	SIAN	600
----	-----	------	-----

Care Instructions

Professional dry clean in situ only			
-------------------------------------	--	--	--

				
---	---	--	---	---