



## TECHNICAL SPECIFICATION SHEET

Range

Seoul
-------

Design

Flat Woven, Chenille
----------------------

Composition  $\pm 3\%$  per Compound

100% Polyester
----------------

Useable Fabric Width (cm)

138
-----

Martindale (rubs)

$> 50,000$
------------

Seam (mm)

Warp	$< 3\text{mm}$	Weft	$< 3\text{mm}$
------	----------------	------	----------------

Tensile (N)

Warp	$\geq 1100\text{N}$	Weft	$\geq 600\text{N}$
------	---------------------	------	--------------------

Tear (N)

Warp	$\geq 90\text{N}$	Weft	$\geq 80\text{N}$
------	-------------------	------	-------------------

Pilling Grade

@2000 rubs	4-5	@5000 rubs	4-5
------------	-----	------------	-----

Bursting (kPa)

n/a
-----

Weight (gsm)  $\pm 5\%$

320
-----

FR Weight (gsm)  $\pm 5\%$

UK	380	SIAN	380
----	-----	------	-----

Care Instructions

    
--