



## TECHNICAL SPECIFICATION SHEET

Range

**Willow**

Design

Flat woven

Composition  $\pm 3\%$  per Compound

85% Polyester, 12% Cotton, 3% Linen

Useable Fabric Width (cm)

138

Martindale (rubs)

>80,000

Seam (mm)

|      |                   |      |                   |
|------|-------------------|------|-------------------|
| Warp | $\leq 3\text{mm}$ | Weft | $\leq 3\text{mm}$ |
|------|-------------------|------|-------------------|

Tensile (N)

|      |         |      |        |
|------|---------|------|--------|
| Warp | > 1000N | Weft | > 700N |
|------|---------|------|--------|

Tear (N)

|      |        |      |       |
|------|--------|------|-------|
| Warp | > 100N | Weft | > 90N |
|------|--------|------|-------|

Pilling Grade

|            |   |            |   |
|------------|---|------------|---|
| @2000 rubs | 4 | @5000 rubs | 4 |
|------------|---|------------|---|

Bursting (kPa)

n/a

Weight (gsm)  $\pm 5\%$

510

FR Weight (gsm)  $\pm 5\%$

|    |     |      |     |
|----|-----|------|-----|
| UK | N/A | SIAN | 590 |
|----|-----|------|-----|

Care Instructions

Professional dry clean in situ only

